

DESCRIPTION

DESCRIPTION			ROCKET
Surface			CLP
Backing			Combined closed cell foam system
Thickness	mm	EN ISO 24346	3,8
Top layer	mm	EN ISO 24340	0,7
Weight	g/m ²	EN ISO 23997	2420
Width	m	EN ISO 24341	2
Standard roll length	kg/m ²	EN ISO 24341	16 or 5 ± 10%

CLASSIFICATION

Product specification		EN 14904 EN 651	Vinyl indoor sports floor
Impact sound insulation	dB	EN ISO 717-2	NA
Thermal resistance	m ² K/W	EN 685	0,03
Reaction to fire	-	EN 13501	C _{fl} -s1


SPORT PROPERTIES

Friction	-	EN 13036-4	80-110
Shock absorption	%	EN 14808	NA
Vertical deformation	mm	EN 14809	0,33
Ball rebound	%	EN 12235	< 90
Specular gloss	%	EN 2813	< 30


TECHNICAL CHARACTERISTICS

Dimensional stability	%	EN ISO 23999	± 0,2
Indentation resistance	mm	EN 1516	< 0,5
Resistance to rolling load	N	EN 1569	1500
Colour fastness	-	EN 13036-4	6
Chemical resistance	-	EN ISO 26987	- no change
Abrasion resistance	mg/1000 cycles	EN ISO 5470-1	< 250



OTHERS



4387



7533



GRABOPLAST LTD.

H-9023 Győr, Fehérvári út. 16/b. Telefon: (+36) 96 506-100
 instagram.com/graboplast | facebook.com/graboplast
 www.grabo1905.com

