

DOMINO SPC ACOUSTIC

Technical datasheet

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction	Rigid modular flooring with SPC core		
Total thickness	EN ISO 24346	mm	4,0 + 1,0
Wear layer thickness	EN ISO 24340	mm	0,4
Plank size	EN ISO 24341	mm	180 x 1250
Tile size	EN ISO 24341	mm	310 x 620
Thickness of IXPE foam	EN ISO 24340	mm	1,0
Total weight	EN ISO 23997	kg/m2	7,8
CLASSIFICATION			
European classification	EN 685	class	23/32/41
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Residual indentation	EN ISO 24343	max. mm	0,1
Dimensional stability	EN ISO 23999	max. %	0,25
Wear resistance IP method A	EN 13329	min. cycles	1200
Fire resistance	EN 13501-1	class	Bfl-s1
Slip resistance	DIN 51130		R10
	EN 13893		DS
Impact sound reduction	EN ISO 717-2	dB	21
Chemical resistance	EN ISO 26987		✓
Light fastness	EN 20105 B02	grade	6
Surface treatment			SILVER KNIGHT iGUARD
VOC emission	ISO 16000		✓
Environmental attributes			Phthalate, Solvent and Heavy metal free product
Content of PCP	EN 12673		does not contain
Formaldehyde emission	ENV 717-1		E1 (no emission)
Warranty	Commercial	year	5
	Residential	year	10
CE MARKING	EN 14041		✓